

Singapore Test Services Pte Ltd

Jurong Head Office: 249 Jalan Boon Lay Singapore 619523 Tel: (65) 6660 7271 / (65) 6660 7322 Fax: (65) 6261 2617

**Bukit Timah Branch Office:** 

601 Rifle Range Road Singapore 588398 Tel: (65) 6460 9171 Fax: (65) 6469 3842

Website: www.test.com.sg E-mail: stsb@ststest.com.sg ( Regn. No.: 198004219D )

Report Title:		Report No:
	Microindentation Hardness Measurement	8450-0412-01231/3
		Page 1 of 1
Client Name:		Client Reference:
	Richport Technology Pte Ltd No. 107 Neythal Road Singapore 628595	PO No. 2012-03-087
Attention to:		Date:
	Mr. Lim Hock Kim	03 April., 2012

Report:

Subject

: To conduct microindentation hardness measurement.

Sample Description

: Sample : Chromium Coating test panel.

Base Material: Mild Steel Received Date: 30/03/12.


Test Method

: ASTM E384-10e2" Knoop and Vickers Hardness of Materials".

**Test Results** 

: As reported below





Points / from edge	100gf / 15 secs	
1 / 25μm	946	
2 / 38µm	973	
3 / 51µm	960	
4 / 64µm	939	
Average	955	

Work Carried Out By:

Reported By:

Approved By:

Choy Foo Kion

Choy Foo Kion

Liu Tie

(No Signature Required)

Snr.Supervisor

Principal Engineer





