



Singapore Test Services

A company of ST Kinetics

Singapore Test Services Pte Ltd

249 Jalan Boon Lay
Singapore 619523
Tel : (65) 6660 7271 / 6660 7322
Fax : (65) 6261 2617
Email: stsb@stengg.com
http ://www.test.com.sg

601 Rifle Range Road
Singapore 588398
Tel : (65) 6460 9171
Fax : (65) 6469 3842
(Regn. No.: 198004219D)

Report Title: Microindentation Hardness Measurement	Report No: 8450-0910-05263C
	Page 1 of 1
Client Name: Richport Technology Pte Ltd No. 107 Neythal Road Singapore 628595	Client Reference: PO No. 2010-09-031
Attention to: Mr. Lim Hock Kim	Date: 23 Sep 2010

Report:

Subject : To conduct microindentation hardness measurement on the surface of the plating.

Sample Description : Sample : Hard Anodizing;
Coating Thickness: 55µm;
Date: 21/09/10.

Test Method : ASTM E384-09 "Standard Test Methods for Microindentation Hardness of Materials".

Test Results : As reported below

Surface Hardness	
Point	100gf / 15 secs
1	413
2	409
3	387
4	428
5	415
Average	410



01/10/10

Work Carried Out By: Choy Foo Kion	Approved By: Liu Tie for Manager
Reported By: Huang Weiting Snr. Engineer	

